



Harionm
Flexipack Industries

An ISO 9001 : 2008 Accredited Company

भारत सरकार के कृषि विभाग द्वारा स्वीकार किया हुआ
किसान भाईयों का भरोसेमंद



खेत तालाब



बारिश का पाणी डॉलर ब्रँड

खेत तालाब में जमा करो...

और अपनी खेती अकाल मुक्त बनाओ...!

भविष्य में खेततालाब से कोई विकल्प नहीं ।

डॉलर ब्रँड खेत तालाब

बनओ और अपनी खेती और बगिचा

बारह महीने फलाओं ।

IS 15351: 2015



CM/L-7500025507

IS- 7903:2011



CM/L-7500090813

डॉलर ब्रँड खेत तालाब बनाने का सही तरीका



प्रथम आप अपने खेत में आपके आकारमान के अनुसार तालाब की खुदाई कर ले । उसमें से नुखिले पत्थर, पेढ , पौधे ऐसी सभी चिजे जो लायनिंग को खराब कर सकती है, वह सब निकाले ।

तालाबा कि खुदाई पुरी होणे के बाद तालाब के बंड की अच्छी तरह से दबाई कर ले । इससे जैसे आप पाणी भरोगे तो लायनिंग पे प्रेशर नही आयेगा ।



खेत तालाब मे लायनिंग अच्छादन करते समय आप लायनिंग हवा से उड ना जाए इसलिए मिट्टी अथवा रेती कि बोरिया भरके तालाब के चारों बांधों के उपर रखिए।

खेत तालाब का जो लायनिंग आया है वह डॉलर ब्रँड का है यह जाँच ले । लायनिंग बिझाते वक्त जो जॉईंट किया जाता है वह अच्छी तरह से किया है क्या नही यह भी जरूर देखिए ।





डॉलर ब्रॅड लायनिंग तालाब के जगह ही फिटींग करना बेहतर होता है । क्योंकि वही फिटींग करने से मॅनपॉवर कम लगती है और फिटींग भी मजबूत होता है ।।

खेत तालाब कि लायनिंग पूरी होने पर आप खुद स्वयं पुरा तालाब घुमके लायनिंग का जाँईट चेक कर ले ताकी कही भी लिकेज ना रहे । इसके बादही धिरे धिरे आप तालाब में पाणी डाल ले ।



तालाब का उपर के बाजू का लायनिंग फिक्स करने के लिए चारो तरफ से एक फिट चौडा और एक फिट उंचा कॅनॉल बनाईये । तालाब मे पाणी डालने के बाद उसी कॅनॉल में लायनिंग के उपर मिट्टी डालके उसे फिक्स किजीए ।

इसी तरह से आपका डॉलर ब्रॅड खेत तालाब अच्छी तरह से पूरा हो जाएगा । उसमे पुरा पाणी भरने के बाद उसकी चारों बाजू से कंपाऊंड करके उसे सुरक्षित रखिए ।



Technical Specification For Pond Liner (As Per IS :15351 :2015)

SR.No	Test Property	Unit	Type 1	Type 2	Type 3	Type 4	Test Method
1	Thickness	MM	0.25	0.5	0.75	1.00	IS : 7016 part 1
2	Mass	g/m ²	250	420	650	950	IS : 7016 part 1
3	Diamenssions (length & width)	-	As declaired + 1 % & No negative Tolerance	As declaired + 1 % & No negative Tolerance	As declaired + 1 % & No negative Tolerance	As declaired + 1 % & No negative Tolerance	Annex A of IS 11652
4	Carbon Black contents (%)	%	2.5± 0.5	2.5± 0.5 %	2.5± 0.5 %	2.5± 0.5 %	IS : 2530
5	Breaking load on 20*10 cm strip,N Min.before UV exposere (Original)warfway	N	3300	6600	8200	10700	IS :13162 part 5
	weftway	N	3000	6000	7400	9700	IS : 13162 part 5
6	Strain (Elongation)at maximum load (%)	%	20± 5	20± 5	20± 5	20± 5	IS :13162 part 5
7	Breaking load on 20*10 cm strip,N Min. after UV exposere of 1000 Hrs	N	80 % of actual original value	80 % of actual original value	80 % of actual original value	80 % of actual original value	Annex B & IS : 13162 part 5
8	Impact failure load at 1524 mm drop, Min gram force at 50 % failure	gram	1150	1840	2875	4025	Annex C IS :15315
9	Tear resistance	N	100	250	300	350	IS :7016 part 3
10	Puncture resistance	N	300	500	725	900	Annex D IS 15351
11	Bursting strength(Ball Burst)	N/cm ²	60	110	135	200	IS : 7016 part 6
12	Seam strength before UV Exposure	N/mm	15	30	40	42	IS :15060
13	Seam strength after UV Exposure	N/mm	80 % of actual original value	80 % of actual original value	80 % of actual original value	80 % of actual original value	IS 15060 & Annex D IS 15351
14	Hydrostatic Resistance (Test specimen with joint) before UV expossure	kg/cm ²	No leakage at 10 kg/cm ²	No leakage at 15 kg/cm ²	No leakage at 20 kg/cm ²	No leakage at 25 kg/cm ²	Annex E IS :15351
15	Hydrostatic Resistance (Test specimen with joint) after UV expossure	kg/cm ²	80 % of actual original value	80 % of actual original value	80 % of actual original value	80 % of actual original value	Annex B & E of IS : 15351
16	Ash content,(%) Max	%	1	1	1	1	Annex F IS :15351

Notes : This document is computer generated and hence no signature is needed.



HARI OM FLEXIPACK INDUSTRIES

Office: GALAXY Business Tower, 3rd Floor, Dabholkar Corner,
Kolhapur. Pin: 416001

Customer Care No. : Vikas - +91- 9623700039, Dhiraj - +91 9370077772

Email: rajesh@packandprint.com

Factory : Pune – Banglore Highway, Behind Rajesh Motors,

A/P – Vathar, Dist. Kolhapur - 416112 State. Maharashtra, INDIA

Customer Care No. : Vikas - +91- 9623700039, Dhiraj - +91 9370077772

E-mail : dhiraj@packandprint.com **Web. :** www.packandprint.com

Authorised Dealer